



To : Bp. Alfred C
 From : R & D Dept.
 Date : 14 July 09
 RE : Test Abrasive

Dengan Hormat ,

Berikut diinformasikan hasil test abrasive dan metode pengujian untuk jenis lacquer Anti Abrasive , Anti Scratch dan Matt lacquer :

No	Jenis Lacquer	Test Abrasive		Standard		Metode	
		Anti Abrasive	Anti Scratch	Anti Abrasive	Anti Scratch	Anti Abrasive	Anti Scratch
1	Anti Abrasive	lwp : - Fwp : 1250 cycles	Losses : -	1000 - 1200 Cycles	Losses 22 - 34 mgr	Load : 500 gr Sand paper : S 33 H18	Load : 1000 gr CS : 10
2	Anti Scratch	lwp : 150 cycles Fwp : 250 Cycles ✓	Losses : 20 mgr				
3	Matt Lacquer	lwp : 194 cycles Fwp : 290 cycles ✓	Losses : 33 mgr				

Terima kasih atas perhatiannya .

Salam,

Sonny HP